

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
15 September 2005 (15.09.2005)

PCT

(10) International Publication Number
WO 2005/084845 A1

(51) International Patent Classification⁷: **B21D 26/02**,
B21C 23/08, 23/00

(74) Agent: **REINHOLD COHN AND PARTNERS**; P.O.
Box 4060, 61040 Tel Aviv (IL).

(21) International Application Number:
PCT/IL2005/000246

(22) International Filing Date: 2 March 2005 (02.03.2005)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/548,865 2 March 2004 (02.03.2004) US

(71) Applicant (for all designated States except US):
MAGTECH-MAGNESIUM TECHNOLOGIES LTD.
[IL/IL]; 7 Ha'ofe Street, Southern Industrial Zone, P.O.
Box 7284, 78172 Ashkelon (IL).

(71) Applicant and

(72) Inventor: **SPINAT, Eli** [IL/IL]; 5 Shapira Street, 64358
Tel Aviv (IL).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **JAEGER, Ste-
fan** [DE/DE]; 22 Aspergstr., 70186 Stuttgart (DE).
BEN-ARTZY, Adi [IL/IL]; P.O. Box 445, 85025 Metar
(IL).

(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,
KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD,
MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG,
PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ,
TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA,
ZM, ZW.


(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,
ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,
FR, GB, GR, HU, IE, IS, IT, LT, LU, MC, NL, PL, PT, RO,
SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN,
GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: AN ARTICLE MADE OF A MAGNESIUM ALLOY TUBE



(57) Abstract: An article made of a magnesium alloy tube (23) is provided, the article having a grain size of between 10µm and 50µm and being manufactured by internal high pressure forming. The temperature of the internal high pressure forming is between 200°C and 605°C. The tube (23) is manufactured by extrusion, wherein the extrusion temperature is between 300°C and 605°C, the extrusion speed is substantially between 5 mm/sec and 45 mm/sec, and the extrusion reduction ratio is substantially between 10:1 and 50:1. The tube (23) may be annealed for 6 hours at 300°C

WO 2005/084845 A1